# A Review of Additive Manufacturing for Ceramic Production

# Introduction

## Economic context

The competition in the world market for manufactured products has intensified tremendously in recent years. In order to swiftly bring products to market, many of the processes involved in their design, test, manufacture and market have been squeezed both in terms of time and material resources. Increasingly demanding consumers have pushed product design and manufacturing towards increased variety and complexity. At the same time, the life time of manufactured products and the lead-time required have been urged to decrease. The efficient use of resources calls for new tools and approaches.

The 20<sup>th</sup> century featured a tendency towards a service-based economy, leading to deindustrialization. As a result, today's European economy is facing a growing challenge to compete with low wage regions, and therefore keeping, or bringing production back inside the Community. In order to regain competitiveness, the manufacturing sector must shift to high-tech industries:

- by moving from resource-based to knowledge-based manufacturing ("Treaty of Lisbon", 2007), and
- by moving from mass-produced single use products to new concepts of higher added value, custom-made, eco-efficient and sustainable products, processes and services. (EU Commission, 2001)

Therefore, the manufacturing sector should invest in:

- Intelligence and efficiency
- High qualified workers
- Changing the way we think and fabricate products
- Being more creative
- Exploring new opportunities
- Producing highly customized products that are difficult to copy

A shift to mass customization, and particularly to mass personalization, its more elaborate version, is pointed as the way to achieve such objectives. As an emerging manufacturing paradigm, it diverges from the mass-produced, single use products by adapting them to their end-user.

### From craft production to mass personalization

Before the industrial revolution, the existing manufacturing paradigm was *craft production*, in which craftsmen would produce objects by hand or using hand-operated utensils. This meant that products took a long time to manufacture, and at a high cost per unit. The industrial revolution in the 19<sup>th</sup> century meant a transition from handcrafted to *mass-produced* objects, leading to an exponential increase in production volume, as well as to a drastic decrease in cost per unit. However, this also led to a drastic decrease in variety. By contrast, craft production allowed for the product to be unique, and adapted to

its user's needs. The industrial machine would produce many more items in much less time, but they were all copies of each other (Hu, 2013).

This trend began to change in the 1960s with the introduction of lean production (Womack et al., 1991). This manufacturing and management paradigm emerged from the automotive industry, which aimed at reducing waste to increase productivity. In lean manufacturing, products would be made-to-order, which meant that they could be adapted to that order before they were produced. Such approach, therefore, led to a new increase in product variety, and paved the way to the next paradigm, mass customization, which would emphasize this tendency even more.

The concept of mass customization has been anticipated by Alvin Toffler in *Future Shock* (1971) and further developed in *The Third Wave* (Toffler, 1980). The new paradigm was coined "*mass customization*" by Stanley Davis (1987), but the methods to implement it were later systematized by B. Joseph Pine II (1993). Since then, the concept has been upgraded. One most commonly cited definition of mass customization is the one by Tseng and Jiao (2001), as "producing goods and services to meet individual customer's needs with near mass production efficiency". A typical application of the mass customization paradigm is offered by sport shoes and automobiles manufacturers, which enable the customer to customize certain components from a defined set of colors. The color selection can be made online, through an automated configuration toolkit, which provides a visualization of the final product according to the customer's selection (Fogliatto et al., 2012).

Recently, the paradigm of mass personalization has emerged, in which products can be tailor-made to individual specific requirements. Mass personalization can be considered one step further from mass customization, "whereas both of these strategies are guided by the criterion of product affordability consistent with mass production efficiencies, the former (mass personalization) aims at a market segment of one while the latter (mass customization) at a market segment of few" (Kumar, 2008, p. 536; Tseng et al., 2010). Also, personalization involves intense communication and interaction between two parties, that is customer and company (Piller, 2014). Examples of mass personalization include manufacturing of prosthetics, which are produced to fit specifically to one given patient. Typically, the region of the patient's body that will receive the prosthetic part is 3D scanned, so that the artificial part fits perfectly (Fiorindo, 2012; Gibson et al., 2010).

Mass personalization responds to the Gothenburg protocol two-fold: by creating custom-made products and services, and by ensuring their sustainability. Mass personalization enables competitiveness by responding to current market demands. Today, consumers want to be treated as individuals - each having specific needs. Products are expected to be tailored to individual taste, "built-to-order" but at prices comparable to those of standard mass-produced goods. Mass-personalized products are more sustainable than their mass-produced counterparts. In fact, some studies seem to indicate that a product that is adjusted to its user will be discarded later, reducing its environmental impact (Diegel et al., 2010).



Figure 1 – Left: Volume variety relationship in manufacturing (Hu et al., 2011) and Right: Relationship between cost per unit and variety

### Additive manufacturing towards mass personalization

Recent developments in digital fabrication, namely additive manufacturing technology are enabling the adoption of mass customization and mass personalization strategies. (Da Silveira et al., 2001; Hu, 2013, p. 6; Piller, 2004; Reeves et al., 2011) Additive manufacturing (AM) is revolutionizing the manufacturing industry by enabling the rapid, flexible, and cost-efficient design and production of products across different applications and industries (Wohlers, 2014), while featuring some important characteristics:

- Additive manufacturing is sustainable, since it typically produces less waste than, for instance, subtractive manufacturing techniques (Diegel et al., 2010). Also, additive manufacturing allows for a product to be manufactured virtually anywhere, as long as there is raw material available, since design is shifting to digital data that can be accessed anywhere in the world in a matter of seconds. This reduces the product's transportation costs, as well as its environmental impact;
- Additive manufacturing offers complexity for free (Hague et al., 2003), as there is no increase of cost when comparing the additive manufacturing of a complex component with a simple one. Therefore, AM technology can be used to product almost any shape;
- Additive manufacturing also offers individuality for free (Dillenburger and Hansmeyer, 2013), since the cost of manufacturing a batch of products that are different from each other is the same as if they were equal. In this case, cost depends solely on quantity of material, not on variation of shape.



Figure 2 - Additive manufacturing: complexity and individuality for free (Aghassi and Witzel, 2014)

## Motivation and methodology

The motivation for this paper is the mass personalization of ceramic tableware. There is an interest for personalization in this sector, as previous studies and projects have shown (CM Alcobaça, 2009; Museros et al., 2004). However, only a few of these have tapped the potential of additive manufacturing as a production system, and only for relatively simple shapes (Huang and Hudson, 2013). In fact, manipulation of the curved shapes typically found in ceramic tableware is all but straightforward. We aim at delivering a sophisticated system that enables the consumer to personalize his or her own ceramic tableware set, through an extended design space in terms of both shape and decoration, while maintaining a captivating experience. Using such a system, each consumer can generate a unique solution according to his or her own needs and taste, and hence the expression "mass personalization" of ceramic tableware is used instead of "mass customization", according to the definition discussed earlier.

The implementation of a mass personalization system (Figure 3) implies the articulation among three sub-systems: design, computer and production, adapting a model proposed by Duarte (2008) for implementing mass customization. A design system based on shape grammars (Stiny and Gips, 1972) is being developed to insure consistent design features amongst all the elements in the set, or collection, as well as to enforce constraints derived from the manufacturing process or ergonomic design guidelines (Castro e Costa and Duarte, 2013). The computer implementation of the design system must cope with the challenges that derive from assigning the role of designer to end-users, who might easily become overwhelmed by the "white canvas syndrome." And finally, the production system must be capable of materializing whatever shape is designed by the end-user. Such need for formal flexibility calls for the use of additive manufacturing.



Figure 3 - Mass personalization implementation model (adapted from Duarte, 2008)

In this paper, we shall focus on the production system of personalized tableware. The first step was to conduct a technology survey on the state-of-the-art concerning additive technology, specifically technology that has been used for the production of ceramic objects. The solutions identified in the survey have been analyzed according to criteria stemming from the requirements of the customization system, in order to determine which technology would be more suitable for our purpose.

# Manufacturing of ceramic objects

Before focusing on the existing additive manufacturing solutions, we present an overview of handicraft techniques for producing ceramic objects. Then we look at how these traditional techniques were

adapted to industrial manufacturing. Finally, we focus on current additive manufacturing technology applied to ceramics, with an emphasis on consumer products such as tableware.



Figure 4 - Typical ceramic manufacturing process (adapted from Hamilton, 1974)

### Ceramics manufacturing process

Either in handcrafted or industrial manufacturing, from simple vases to geometrically complex and intricately decorated sculptures, the making of every ceramic piece goes through a similar sequence (Figure 4): after preparing the clay, and while it remains in its plastic state, the ceramic object is given its shape, as well as its decoration, if based on reliefs (three-dimensional decoration). The object is then dried, and fired a first time, resulting in what is called the biscuit. The biscuit is then covered with glaze, which grants it the shiny look and smooth texture that is typical of tableware ceramics. If the piece is to be painted or decaled, such two-dimensional decoration is applied before the glazing. After glazing, the ceramic object is fired once more. For plain ceramic tableware, without any decoration, after manufacturing process would stop here. Alternatively, the piece may be given on-glaze decoration, after which it must be fired one last time.

Since the objective of the mass customization system is to manipulate the shape of the tableware elements, 2D-decoration after biscuit firing and on-glaze decoration will not be addressed, and we will focus our attention on the forming or modelling phase.

## Handicraft ceramic modelling

There are several traditional techniques for modelling ceramic objects, namely tableware elements. Hand methods of forming clay include coiling, and throwing. (Figure 5) Coiling consists of making coils out of clay, and stacking them on top of each other. The surface of an object made by coiling is revealing of the process used, and is typically smoothed by hand or using proper utensils. Throwing is probably the most recognizable of the handicraft shaping techniques, in which hand pressure is applied on a ceramic piece that is rotating on a device, the potter's wheel (Hamilton, 1974).



Figure 5 - Handicraft ceramic modelling techniques: coiling (left), and throwing (right) (Quinn, 2007 © Quarto Publishing plc)

Moulding methods of forming clay include pressing and slip casting (Figure 6). These methods make use of plaster moulds that hold the negative shape of the desired object. Pressing consists of manually pressing clay in its plastic state against the mould, so its shape is transferred to the clay. In slipcasting, a suspension of clay in water – the slip – is poured inside the mould (Hamilton, 1974). Other moulding methods include jiggering and jolleying (Figure 6), which consist of forcing a piece of clay to shape against a plaster mould through rotation, similarly to throwing on the potter's wheel. This technique is suitable for producing revolution-based open ceramic pieces, such as circular plates (jiggering) and bowls (jolleying) (Quinn, 2007).



Figure 6 - Mould-based traditional techniques, from left to right: pressing by hand, (Hamilton, 1974), slipcasting, jiggering and jolleying (Quinn, 2007 © Quarto Publishing plc)

## Industrial ceramic modelling

Some of these traditional techniques were adapted into an industrial context, boosting their productivity. Roller machines make use of a heated metallic mould and a plaster die, which rotate while pressing a piece of clay into the desired shape. Roller machines allow for low production costs per unit,

making them ideal for producing large batches (Rado, 1988). Industrial slip casting is not very different from the traditional handicraft version. Of all industrial techniques, slip casting is the one that enables greater freedom of shape. Therefore, such technique is typically used for smaller production batches (Rado, 1988). Plastic pressing, or "ram" pressing, as well as isostatic pressing, or dust pressing, consists of shaping a piece of clay between two permeable plaster dies that are pressed together. This technique is typically used for shaping non-round objects, which would otherwise be produced in roller machines. (Rado, 1988). Therefore, in terms of shape, pressing is more flexible than roller making, but less than slip casting.

All these industrial methods are designed for mass production of ceramic objects. Slip casting, which is typically used for producing the smallest batches, is considered to be profitable for a minimum of a few hundred pieces sharing the same mold. Such quantity is still too large for mass personalization. Even if a customer is buying a large dinner set, it is very unlikely that it will contain more than 24 elements of the same type, and some of them, such as trays or tureens, will be no more than three. As such, for producing such small batches, we should look into current additive manufacturing techniques.

# Additive manufacturing applied to ceramics

Along with the recent developments of additive manufacturing technologies, especially with the rise of consumer-oriented equipment, the term "3d printing" is often used to refer to those technologies. In fact, a Google search for "3d printing" produces more results than one for "additive manufacturing" (Wohlers and Caffrey, 2014). Nevertheless, for the purpose of this research, the industrial standard is used. Therefore, and according to ASTM International Committee F42 on Additive Manufacturing Technologies, additive manufacturing (AM) is defined as the process of joining materials to make objects from 3D model data, usually layer upon layer, as opposed to subtractive manufacturing methods (ASTM F42 Committee, 2012). Also, according to the ASTM F42 Committee, additive manufacturing processes can be sorted into seven categories:

- Material extrusion—an additive manufacturing process in which material is selectively dispensed through a nozzle or orifice;
- Material jetting—an additive manufacturing process in which droplets of build material are selectively deposited;
- Binder jetting—an additive manufacturing process in which a liquid bonding agent is selectively deposited to join powder materials;
- Sheet lamination—an additive manufacturing process in which sheets of material are bonded to form an object;
- Vat photopolymerization—an additive manufacturing process in which liquid photopolymer in a vat is selectively cured by light-activated polymerization;
- Powder bed fusion—an additive manufacturing process in which thermal energy selectively fuses regions of a powder bed;
- Directed energy deposition—an additive manufacturing process in which focused thermal energy is used to fuse materials by melting as the material is being deposited.

Except for directed energy deposition, every one of these processes has been applied to the manufacturing of ceramic objects, and most of them are commercially available. A technology survey was conducted in order to assess the availability and advantages of each of these processes.

We have clustered the technologies and available equipment according to its suitability for producing tableware. In fact, most of the AM technologies are applied to ceramics for the production of precision components, such as electronics, etc. Two processes emerge as the most adequate for our purposes: binder jetting and material extrusion.

### Material extrusion

Material extrusion is probably the best known AM technology. The expiration of patents on material extrusion, namely of Fused Deposition Modeling, is behind the current dissemination of low-cost 3D printers (Wohlers and Caffrey, 2014). Extrusion of ceramic material has been explored both in academia and in design practices. Different projects have studied the constraints and explored the potential of extruding ceramic paste through a nozzle to build objects. In a way, these approaches invoke the traditional techniques of coiling and throwing.

Belgium-based design practice Unfold developed a system from a RepRap 3D printer (Unfold, 2009). Originally, the RepRap machine was designed to extrude polymeric materials, just like so many of the 3D printers that have emerged in recent years. By modifying the extrusion head in order to extrude white clay, they have managed to produce ceramic objects from digital models through additive manufacturing (Figure 7, left). Ceramics artist and educator Tom Lauerman also made use of a RepRap printer, the Prusa i3, for producing ceramic objects (Lauerman, 2014).

A similar approach was tested at IAAC by a team of students in their project Fabclay (Jokić et al., 2012). In this project, a robotic arm was used to control the position of the extrusion head, depositing several layers of clay, thus producing the intended ceramic object (Figure 7, right). Despite the many degrees of freedom provided by the use of a robotic arm, in this project this equipment was used to replicate the movements of a Cartesian 3D printer, i.e., XYZ translation. In this case, red clay was extruded instead of white clay, which was used by Unfold.

Recently, ceramic designers experimenting with additive manufacturing have moved from Cartesianstyle to delta-style printers. In the vast majority of 3d printers, the mechanism for positioning the extrusion head corresponds to a Cartesian manipulator, in which joints correspond to the X, Y and Z Cartesian directions (Craig, 1989). On the other hand, delta-style printers' kinematic configuration corresponds to a linear delta robot (also known as Linapod), in which the extrusion head is positioned by three vertical linear actuators (Merlet, 2006). Because the actuators are identical, such a machine is actually easier to implement (Boer et al., 2012). Both US-based Jonathan Keep (2013) and the Netherlands-based Olivier van Herpt (2014) have used a delta printer to extrude clay and produce large ceramic objects (Figure 8).

Alongside these projects, equipment suppliers have developed ceramic extrusion machines based on the delta robot configuration. Recently, two ceramic 3D printers have entered the market: PotterBot (DeltaBots, 2015), and DeltaWASP 20 40 (WASP, 2015). The DeltaWASP machine works in a very similar way to the machines used by both Jonathan Keep and Olivier van Herpt. In fact, previous collaborations between WASP and Jonathan Keep (Keep, 2014) suggest he operated actual prototypes of the DeltaWASP. In this machine, the delta robot positions the extrusion head along the successive layer paths that build the object. This machine can produce objects as wide as 200 mm, and up to 400 mm tall. The Potterbot, on the other hand, features a static extrusion head, while the build platform and the actual object are manipulated by a delta robot located under the build platform. Potterbot can print objects up to 17 inches (431.8 mm) tall, and 8.75 inches (222.25 mm) wide.



Figure 7 – From left to right: extrusion of white clay objects by Unfold, Belgium (Photo courtesy of Unfold, ©Z33, photo by Kristof Vrancken) and of red clay object by Fabclay, Spain (2012)



Figure 8 – From left to right: extrusion of tall ceramics objects by Jonathan Keep, United States (2013) and by Olivier Van Herpt, The Netherlands (2014)

## Material jetting

France-based company CeraDrop supplies a machine called CeraPrinter, which produces Printed Electronics through material jetting (Ceradrop, 2013). The system is able to deposit a wide range of inks, although none of them are ceramic-based, despite the name suggestion. However, the system is able to print on ceramic substrates, but it is unsuitable to produce ceramic objects. In fact, the maximum dimensions of the produced parts must fit in in a 305 mm wide, 10 mm thick square, dimensions which are adequate for electronics, but not for manufacturing tableware. Nevertheless, CeraPrinter is the only surveyed equipment using material jetting technology and ceramic materials, and therefore was included in this analysis.

## Binder jetting

In recent years, several research teams have been exploring the possibility of using the binder jetting principle for manufacturing ceramic objects, either on the hardware side (Hoskins, 2012; Universidade de Aveiro, 2013) or on the material side (Figulo, 2013; Tethon 3D, 2014). The common starting point for

these projects was the 3D Printer, a machine developed at MIT in the 1990s, that later justified the spinoff of ZCorporation, and is now part of the 3DSystems product family. Originally, the 3D Printer produced objects by jetting a cyanoacrylate-based binder onto layers of a plaster-based powder. By using the same process but replacing the plaster-based material with ceramic powder, these teams have been able to produce detailed green ceramic objects, which can then follow up on their typical production process, through firing in the kiln, glazing, etc. (Figure 4).

Currently, ceramic binder jetting appears to have moved from the research to the commercial domain. In the 2014 edition of Consumer Electronics Show (CES), US-based company 3DSystems announced CeraJet, a "3D printer" that produces ceramic objects. This equipment is allegedly suitable for producing large ceramic objects, such as tableware, although the dimensions of its build envelope have not been revealed. At the time, its commercialization was announced for the second half of 2014, although according to current information on the company's website, it is postponed to 2016 (3DSystems, 2014). 3D Systems first entered the world of ceramics in December 2013 by acquiring Figulo, a Boston-based company that produced ceramic parts using binder jetting (Wohlers and Caffrey, 2014). Shortly after, 3D Systems announced they would commercialize the CeraJet ceramics 3d-printer.

### Lamination

US-based company CAM-LEM applied lamination technology to the production of ceramic and metal components for microfluidic applications and technologies, through a machine called CL-100 (CAM-LEM, 2005). According to the company, the maximum build size is a 150 mm cube. However, no further technical information is available on the company's website. Nonetheless, both the explanation of the process and samples on the website suggest that this technology would be more suitable for objects featuring vertical, rather than oblique or curved, surfaces. As such, it would most likely be inadequate for producing tableware.

### Vat photopolymerization

Several companies are currently supplying equipment for additive manufacturing of ceramics through vat photopolymerization.

CeraFab 7500 is supplied by Austria-based company Lithoz. According to the company, this printer is suitable for producing high-performance ceramic objects, namely cost-effective prototypes, small scale series and complex parts, through its proprietary LCM technology (Lithoz GmbH, 2012). The build envelope is rather small – 76 x 43 x 150 mm.

CeraMaker applies laser stereolithography to ceramics, and it is supplied by France-based company 3DCeram. According to the company, this printer is particularly suitable for manufacturers of ceramic parts, integrators or end-users of ceramic parts, players in the luxury or biomedical industries, but also in the industry in general (3DCeram, 2014). In comparison with the previous example, the build envelope is larger –  $300 \times 300 \times 110$  mm.

Italy-based company Digital Wax Systems is launching the DWS XFab, which applies laser stereolithography to several materials, including a "ceramic nano-filled" composite, (Digital Wax

Systems, 2014), which is unsuitable for producing tableware. This machine is marketed as a consumeroriented 3d printer, costing around US\$ 5,000 (Wohlers and Caffrey, 2014). Its work area is limited to a cylinder that is 180 mm wide and tall.

K20 is a piece of equipment that applies laser stereolithography to composite materials of ceramics and metal, supplied by France-based company Prodways (2013). The maximum build area is a box of 150 x 560 x 150 mm. The focus on composite materials suggests that such equipment might be less suitable for producing mono-material ceramic objects.

## *Powder bed fusion / sintering*

Phenix, a France-based company, recently acquired by 3D systems, supplies equipment for laser sintering of metal and ceramic powders (3DSystems, 2013). The build envelope for the most capable machine that deals with ceramics, the ProX-200, is 140 x 140 x 100 mm.

Chinese company Wuhan Binhu develops sintering systems for several different materials including three ceramic powders (Wohlers and Caffrey, 2014). The maximum build size for producing ceramic parts is a 500 mm square, 400 mm high. Although this build envelope is large enough for producing most of the elements of a complete tableware set, typical costs for sintering technology suggests that this option is not competitive.

### Directed energy deposition

During this survey, we have not found any application of directed energy deposition in ceramics.

### Comparative analysis of AM technology

From the survey presented above, and as summarized in Table 1, we verify that most of the AM processes and equipment are focused on the production of high-performance precision parts, compromising their suitability for production of tableware.

Process	Supplier	Equipment	Dimensions (wxlxh mm)			Equipment cost *
Material	WASP	DeltaWASP	200 2	200 4	00	€ 2,370
extrusion	DeltaBots	PotterBot	222 2	222 4	32	€ 3,175
Material jetting	CeraDrop	CeraPrinter	305 3	805 1	00	€ 175,000
Binder jetting	3D Systems	CeraJet	N/A N	I/A N	/A	€ 9,200
Lamination	CAM-LEM	CL-100	150 1	50 1	50	N/A
Vat photo	Lithoz	CeraFab	76 4	3 1	50	
polymerization	3DCeram	CeraMaker	300 3	800 1	10	€ 290,000
	Digital Wax Systems	DWS Xfab	180 1	.80 1	80	€ 5,000
	Prodways	К20	150 5	60 1	50	
Powder bed	3Dsystems (Phenix)	ProX-200	140 1	40 1	00	€ 200,000
fusion	Wuhan Binhu	HRPS-IV	500 5	500 4	00	€208,000
Directed energy deposition		N/A				
Reference for dimensions			270 2	70 16	50	

#### Table 1 - Summary of Additive Manufacturing equipment for ceramics

(standard dinner plate dimensions) (standard teapot height)

\* estimated cost values, either from quote requests to suppliers or press releases; values have been normalized to euro (€)

The first limitation is set by the dimensions of the building envelopes. A standard dinner plate, for example, which typically measures 27 cm in diameter and 3 cm in height, would not fit in more than half of the surveyed machines. The ones where a plate would fit could not accommodate a standard 35 cm tray or a teapot, which can be 16 cm tall. The only exception is the Laser Sintering equipment from Wuhan Binhu.

The second limitation is set by the cost of printing tableware elements, namely of the printing materials. In fact, some of the contacted equipment suppliers actually considered it unsuitable for producing ceramic tableware elements, mainly because the ceramic materials are mostly alumina-based. These materials are developed to meet demanding technical characteristics, and therefore expensive when compared to the material typically used for producing tableware.

In general, we conclude that most of the commercially available solutions are unsuitable for producing mass customized tableware. Two processes, nevertheless, stand apart from these technologies: binder jetting, and material extrusion.

Binder jetting is currently being established as the *de facto* standard for ceramic additive manufacturing. In fact, several print-on-demand companies (Shapeways, i.Materialise, Ponoko, and Figulo, now owned by 3DSystems) are outsourcing this technology to supply ceramic "3D prints" to clients over the internet. However, the cost of such pieces is still high. As with the 3D Printer, also supplied by 3DSystems, the materials to be used with the CeraJet are likely to be proprietary – and therefore quite expensive, if the material price range is similar to the original 3D Printers. Printer owners might try their own materials, but at the risk of damaging the printer and, since the used materials were not recommended by the equipment manufacturer, its warranty would be void. Therefore, using this equipment in the production system of personalized tableware might represent a disadvantage, for a company adopting such an approach would depend on a single supplier and imply rather high material costs.

The material extrusion approaches covered earlier handle this particular problem quite well. In all projects, the extruded material is a ceramic paste mixed by the machine's user. This mix must be fine-tuned in terms of viscosity and others properties, but when the right mix is achieved it can be replicated. This "open-source" approach sets material extrusion apart from the other AM processes.

However, ceramic extrusion presents challenges that must be addressed. In all of the projects referred to, we could identify two factors that could be improved. The first one is the expression of the layers in the manufactured objects. Such texture reveals the nature of the layering process used to make the object. Although in some cases this texture can be desired or even taken advantage of by the designer, it would be important to avoid it in other cases. The second factor relates to the shape of the produced object. In fact, all printed objects possess a somewhat vertical geometry. Although not stated by the authors, this can be identified as a way of avoiding the need for support structures. Consider that we wanted to manufacture a dinner plate using any of the extrusion techniques mentioned above. Without

using a supporting structure, the plate would likely collapse during its manufacturing process. However, supporting structures should be avoided, since they imply more material consumption and require time for their removal. Also, removing support structures usually leads to minor imperfections on the model (Smyth, 2014). Therefore, it would be desirable to overcome this limitation. In the 3D-printing community, the so-called 45-degree rule is often used to address this problem. This rule-of-thumb states that "overhangs that are greater than 45 degrees will need support material or you need to use clever modeling tricks to get the model to print" (France, 2013). The rule suggests that support structures can often be avoided through clever geometry.

# Conclusion

In this paper, we have addressed the potential of mass personalization for ceramic tableware. We have argued that additive manufacturing is the most adequate approach for the production of such objects. Furthermore, we have reviewed the manufacturing of ceramic tableware objects, and assessed which available additive manufacturing technologies would be suitable for that purpose. Based on this assessment, we are developing a conceptual design of a machine for the production of ceramic tableware objects through material extrusion. The design of the machine is based on the experiments with clay extrusion described above and it aims to overcome what has been identified as the two major challenges in clay extrusion: the need for supporting structures, and visible layer expression. The design, development and testing of such machine will be the subject of a future publication.

The main objective of this research is to implement such a mass personalization system in an industrial context, for which contacts with companies in the ceramic sector have been established. Under such partnership, we expect to build a prototype of the machine under development, in order to test it and assess its suitability for the manufacturing of personalized ceramic tableware.

# Acknowlegments

This work is funded by FEDER Grants through COMPETE – Programa Operacional Factores de Competitividade and by National Grants through FCT – Fundação para a Ciência e a Tecnologia, as part of the "TECTON 3D" project (PTDC/EEI-SII/3154/2012). Eduardo Castro e Costa is funded by FCT with PhD grant SFRH/BD/88040/2012. Furthermore, the authors would like to thank the team at the University of Manchester, namely Dr. Marco Domingos at the Manchester Biomanufacturing Centre, and Dr. Christian Griffiths and Mr. Stuart Mcintyre at the School of Mechanical, Aerospace and Civil Engineering.

## References

3DCeram. (2014), "Ceramaker - Print Ceramic by yourself", Ceramaker, available at:

http://www.ceramaker.com (accessed 14 November 2014).

- 3DSystems. (2013), "Phenix Systems", available at: http://www.phenix-systems.com/en (accessed 14 November 2014).
- 3DSystems. (2014), "CeraJet<sup>™</sup>, www.3dsystems.com, Text, , 25 March, available at: http://www.3dsystems.com/de/cerajet (accessed 14 November 2014).
- Aghassi, S. and Witzel, J. (2014), *Facing the Future: Additive Manufacturing Call for Partners: Consortium Study*, Knowledge Exchange AG / Fraunhofer Institute for Production Technology, available at: http://www.ilt.fraunhofer.de/content/dam/ilt/de/documents/zentren-undcluster/konsortialstudien/Consortium-Study-on-Additive-Manufacturing.pdf.
- ASTM F42 Committee. (2012), *Terminology for Additive Manufacturing Technologies*, ASTM International, available at: http://www.astm.org/Standards/F2792.htm (accessed 24 October 2014).
- Boer, C.R., Molinari-Tosatti, L. and Smith, K.S. (2012), *Parallel Kinematic Machines: Theoretical Aspects* and Industrial Requirements, Springer Science & Business Media.
- CAM-LEM. (2005), "CAM-LEM", CAM-LEM, available at: http://www.camlem.com/camlemprocess.html (accessed 14 November 2014).
- Castro e Costa, E. and Duarte, J.P. (2013), "Tableware Shape Grammar", in Stouffs, R. and Sariyildiz, S. (Eds.), *Computation and Performance Proceedings of the 31st eCAADe Conference*, Vol. 2, presented at the eCAADe, Faculty of Architecture, Delft University of Technology, Delft, The Netherlands, pp. 635–644.
- Ceradrop. (2013), "Ceraprinter", Ceraprinters, available at: http://www.ceradrop.fr/en/products/ceraprinters.html (accessed 14 November 2014).
- CM Alcobaça. (2009), Análise SWOT Do Sector Da Cerâmica Na Região Do Oeste, Gabinete da Presidência, Câmara Municipal de Alcobaça, available at: http://www.cm-

alcobaca.pt/resources/4ca2702efaebf9e29c7c69aa1d0f240a/Ceramica\_SWOT\_INTELI\_Jun2009. pdf (accessed 12 July 2013).

- Craig, J.J. (1989), *Introduction to Robotics: Mechanics and Control*, 2nd ed., Addison-Wesley Longman Publishing Co., Inc., Boston, MA, USA, available at: http://wcms.inf.ed.ac.uk/ipab/rss/lecturenotes-2014-2015/JJCraigRoboticsIntro.pdf.
- Da Silveira, G., Borenstein, D. and Fogliatto, F.S. (2001), "Mass customization: Literature review and research directions", *International Journal of Production Economics*, Vol. 72 No. 1, pp. 1–13.
- Davis, S.M. (1987), Future Perfect, Addison-Wesley.
- DeltaBots. (2015), "3D PotterBot Clay 3D Printer and Ram", *DeltaBots*, available at: http://www.deltabots.com/products/potterbot (accessed 30 July 2015).
- Diegel, O., Singamneni, S., Reay, S. and Withell, A. (2010), "Tools for Sustainable Product Design: Additive Manufacturing", *Journal of Sustainable Development*, Vol. 3 No. 3, p. P68.
- Digital Wax Systems. (2014), "DWS LAB XFAB", DWS LAB, available at: http://dwslab.com/xfab/ (accessed 14 November 2014).
- Dillenburger, B. and Hansmeyer, M. (2013), "The Resolution of Architecture in the Digital Age", in Zhang, J. and Sun, C. (Eds.), *Global Design and Local Materialization*, Springer Berlin Heidelberg, pp. 347–357.
- Duarte, J.P. (2008), *Synthesis Lesson Mass Customization: Models and Algorithms Aggregation Exams*, Agregação, Faculdade de Arquitectura, Universidade Técnica de Lisboa, Lisboa.

Figulo. (2013), "FIGULO", FIGULO, available at: http://www.figulo.com/ (accessed 14 November 2014).

EU Commission. (2001), "Communication from the Commission A Sustainable Europe for a Better World: A European Union Strategy for Sustainable Development (Commission's proposal to the Gothenburg European Council)", available at: http://eur-lex.europa.eu/legalcontent/EN/TXT/?uri=CELEX:52001DC0264.

- Fiorindo, F. <1986>. (2012), "Additive Manufacturing Opportunities: Mass Customization in the Biomedical Industry", available at: http://dspace.unive.it/handle/10579/2146 (accessed 22 July 2015).
- Fogliatto, F.S., da Silveira, G.J.C. and Borenstein, D. (2012), "The mass customization decade: An updated review of the literature", *International Journal of Production Economics*, Vol. 138 No. 1, pp. 14–25.
- France, A.K. (2013), "Top Ten Tips: Designing Models For 3D Printing", MAKE, 11 December, available at: http://makezine.com/2013/12/11/top-ten-tips-designing-models-for-3d-printing/ (accessed 4 December 2014).
- Gibson, D.I., Rosen, D.D.W. and Stucker, D.B. (2010), "Medical Applications for Additive Manufacture", Additive Manufacturing Technologies, Springer US, pp. 400–414.
- Hague, R., Campbell, I. and Dickens, P. (2003), "Implications on design of rapid manufacturing", *Proceedings of the Institution of Mechanical Engineers, Part C: Journal of Mechanical Engineering Science*, Vol. 217 No. 1, pp. 25–30.
- Hamilton, D.D. (1974), *The Thames & Hudson Manual of Pottery and Ceramics*, Thames & Hudson Ltd, New York, N.Y.
- van Herpt, O. (2014), "Functional 3D Printed ceramics", *Olivier Van Herpt*, available at: http://oliviervanherpt.com/functional-3d-printed-ceramics/ (accessed 24 October 2014).

Hoskins, S. (2012), "Towards a new ceramic future", Ceramic Review, Vol. 255, pp. 64–65.

- Hu, S.J. (2013), "Evolving Paradigms of Manufacturing: From Mass Production to Mass Customization and Personalization", *Procedia CIRP*, Vol. 7, pp. 3–8.
- Hu, S.J., Ko, J., Weyand, L., ElMaraghy, H.A., Lien, T.K., Koren, Y., Bley, H., et al. (2011), "Assembly system design and operations for product variety", *CIRP Annals Manufacturing Technology*, Vol. 60 No. 2, pp. 715–733.

- Huang, M. and Hudson, A. (2013), "Sake Set Creator", *Shapeways.com*, 14 February, available at: www.shapeways.com/creator/sake-set/ (accessed 14 February 2013).
- Jokić, S., Lara, S. and Fashami, N. (2012), "FabClay", *FabClay*, available at: http://www.fabclay.com/about (accessed 28 August 2013).
- Keep, J. (2013), "Make your own 3D delta printer for ceramic", 5 September, available at: http://www.keep-art.co.uk/Self\_build.html (accessed 24 October 2014).
- Keep, J. (2014), "WORKING WITH WASProject, ITALY", *Jonathan Keep*, 7 September, available at: http://www.keep-art.co.uk/journal\_14ma.html (accessed 30 July 2015).
- Kumar, A. (2008), "From mass customization to mass personalization: a strategic transformation", International Journal of Flexible Manufacturing Systems, Vol. 19 No. 4, pp. 533–547.
- Lauerman, T. (2014), "Open Source Shout Out (& my first D.I.Y. 3D printer)", *Tom Lauerman*, 24 August, available at: http://www.tomlauerman.com/news-blog/2014/8/24/first-attempt-diy-printer (accessed 31 July 2015).
- Lithoz GmbH. (2012), "CeraFab 7500", *CeraFab* 7500, available at: http://www.lithoz.com/en/products/cerafab-7500/ (accessed 14 November 2014).
- Merlet, J.P. (2006), Parallel Robots, Springer Science & Business Media.
- Museros, L., Mira, J., Sanz, V., Monzó, M., Berndt, D., Schmidt, N. and Brücher, M. (2004), "DIGIMOULD -Digital Moulding for the ceramic industry: a contribution to mass customization", *QUALICER 2004: VIII World Congress on Ceramic Tile Quality*, presented at the QUALICER 2004: VIII World Congress on Ceramic Tile Quality, Camara Oficial de Comercio, Industria y Navegacion, pp. 203– 218.
- Piller, F.T. (2004), "Mass Customization: Reflections on the State of the Concept", International Journal of Flexible Manufacturing Systems, Vol. 16 No. 4, pp. 313–334.

- Piller, F.T. (2014), "Glossary: Key Terms Defined", *Prof. Frank Piller of RWTH Aachen TIM Group*, available at: http://masscustom.info/key-terms-defined/ (accessed 1 December 2014).
- Pine, B.J. (1993), Mass Customization: The New Frontier in Business Competition, Harvard Business Press, Boston, MA.
- Prodways. (2013), "K20 Producer for composite ceramic and metal materials", *Prodways The New Way* of Producing, available at: http://www.prodways.com/en/3d-printer/our-range-of-3dprinters/k20-producer-for-composite-ceramic-and-metal-materials/ (accessed 14 November 2014).

Quinn, A. (2007), The Ceramics Design Course: Principles, Practice, Techniques, Quarto Publishing plc.

- Rado, P. (1988), *An Introduction to the Technology of Pottery*, 2 edition., Pergamon Press, Oxford Oxfordshire ; New York.
- Reeves, P., Tuck, C. and Hague, R. (2011), "Additive Manufacturing for Mass Customization", in Fogliatto, F.S. and Silveira, G.J.C. da (Eds.), *Mass Customization*, Springer London, pp. 275–289.
- Smyth, M.C.T. (2014), Functional Design for 3D Printing: Designing 3D Printed Things for Everyday Use an Engineering Handbook, 1st Edition edition., CreateSpace Independent Publishing Platform.
- Stiny, G. and Gips, J. (1972), "Shape Grammars and the Generative Specification of Painting and Sculpture", in Freiman, C.V. (Ed.), *Information Processing 71*, North Holland, Amsterdam, pp. 1460–1465.
- Tethon 3D. (2014), "Tethon 3D", *Tethon3D*, available at: http://tethon3d.com/ (accessed 14 November 2014).
- Toffler, A. (1971), Future Shock, Bantam Books, New York, NY.
- Toffler, A. (1980), The Third Wave, Morrow.
- "Treaty of Lisbon". (2007), , available at: http://eur-lex.europa.eu/legalcontent/EN/TXT/?uri=CELEX:12007L/TXT.

- Tseng, M.M. and Jiao, J. (2001), "Mass Customization", in Salvendy, G. (Ed.), Handbook of Industrial Engineering, John Wiley & Sons, Inc., pp. 684–709.
- Tseng, M.M., Jiao, R.J. and Wang, C. (2010), "Design for mass personalization", *CIRP Annals Manufacturing Technology*, Vol. 59 No. 1, pp. 175–178.
- Unfold. (2009), "L'Artisan Electronique", available at: http://unfold.be/pages/projects/items/I%E2%80%99artisan-electroniqu (accessed 28 August 2013).
- Universidade de Aveiro. (2013), "PrintCer3D Fabrico rápido de produtos em porcelana por impressão tridimensional", available at: https://www.ua.pt/esan/PageText.aspx?id=17910 (accessed 13 May 2014).
- WASP. (2015), "DeltaWASP 20 40", available at: http://www.personalfab.it/en/products/deltawasp-20-40/ (accessed 30 July 2015).
- Wohlers, T. (2014), "Tracking Global Growth in Industrial-Scale Additive Manufacturing", *3D Printing and Additive Manufacturing*, Vol. 1 No. 1, pp. 2–3.
- Wohlers, T. and Caffrey, T. (2014), Wohlers Report 2014 3D Printing and Additive Manufacturing State of the Industry Annual Worldwide Progress Report.
- Womack, J.P., Jones, D.T. and Roos, D. (1991), *The Machine That Changed the World : The Story of Lean Production*, Harper Perennial.